

Development of the Self Compacting Concrete By Industrial Waste (Red Mud)

Mohan Kushwaha¹, Dr. Salim Akhtar², Survesh Rajput³

¹(Department of civil Engineering, RGPV Bhopal ,India)

²(HOD., Department of civil Engineering, RGPV Bhopal, India)

³(Prof., Department of civil Engineering, MANIT, Bhopal ,India)

ABSTRACT

Self-compacting concrete (SCC) is an innovative concrete that does not require vibration for placing and compaction. It is able to flow under its own weight, completely filling formwork and achieving full compaction, even in the presence of congested reinforcement. The hardened concrete is dense, homogeneous and has the same engineering properties and durability as traditional vibrated concrete. Due to industrialization there is huge amount of red mud created. Aluminum is now consumed during manufacture red mud, which is used. Red Mud is industrial waste and causing threat to environment so the reduce the cost of the construction also to make structure more durable, reduce problem of this material the project has been undertaken so that it can be used for construction fashion of the concrete by blending or by replacing the cement by Red mud.

Keywords - Self-compacting concrete, industrial waste, modified concrete

I. INTRODUCTION

Development of self-compacting concrete (SCC) is a desirable achievement in the construction industry in order to overcome problems associated with cast-in-place concrete. Self compacting concrete is not affected by the skills of workers, the shape and amount of reinforcing bars or the arrangement of a structure and, due to its high-fluidity and resistance to segregation it can be pumped longer distances (Bartos, 2000). The concept of self-compacting concrete was proposed in 1986 by professor Hajime Okamura (1997), but the prototype was first developed in 1988 in Japan, by professor Ozawa (1989) at the University of Tokyo. Self-compacting concrete was developed at that time to improve the durability of concrete structures. Since then, various investigations have been carried out and SCC has been used in practical structures in Japan, mainly by large construction companies. Investigations for establishing a rational mix-design method and self-compactability testing methods have been carried out from the viewpoint of making it a standard concrete.

Self-compacting concrete is cast so that no additional inner or outer vibration is necessary for the compaction. It flows like "honey" and has a very smooth surface level after placing. With regard to its composition, self-compacting concrete consists of the same components as conventionally vibrated concrete, which are cement, aggregates, and water, with the addition of chemical and mineral admixtures in different proportions. Usually, the chemical admixtures used are high-range water reducers (superplasticizers) and viscosity-modifying agents, which change the rheological properties of concrete. Mineral admixtures are used as an extra fine material, besides cement, and in some cases, they replace cement. In this study, the cement content was partially replaced with mineral admixtures, e.g. fly ash, slag cement, and silica fume, Red Mud admixtures that improve the flowing and strengthening characteristics of the concrete.

II. EXPERIMENTAL PROCEDURE

2.1 GENERAL

The main aim of this experimentation is to find out the effect of addition of red mud, which is a waste product from the aluminum industries, on the properties of self compacting concrete containing three admixtures. In this experimentation combinations of admixtures which is taken super plasticizer + VMA.

2.2 MATERIALS USED

In the experimentation PPC was used. Locally available sand and coarse aggregates were used. The specific gravity of sand was found to be 2.55 and was Zone II sand. The specific gravity of coarse aggregates used was found to be 2.61. The coarse aggregates were 12mm and downsize. The mix proportion adopted in the experimentation was 1:1:0.5 with a water/binder ratio 0.31. The flyash/cement ratio used was 1:3.5. The flyash used in the experimentation is pozzocrete 60 was obtained from DIRK INDIA PRIVATE LTD. The chemical composition of flyash is shown in the TABLE- 1

TABLE-1 Chemical composition of flyash.
(Mauskar 2006)

Oxides	Percentages
SiO ₂ +Al ₂ O ₃ + Fe ₂ O ₂	70 min
SiO ₂	35 min
Reactive silica	20 min
MgO	05 max
SO ₃	03 max
Na ₂ O	1.5 max
Total chlorides	0.05 max

The red mud used in the experimentation was obtained from HINDALCO, Belgaum. The fineness of red mud was found to be 35 m²/gm with particle size of 75 microns and its density is found to be 3gm/cc. The chemical composition of red mud is shown in TABLE- 2

TABLE-2 Chemical composition of red mud.
(Mauskar 2006)

Chemical Composition	Bauxite Residue (%)	Typical values Worldwide (%)
Fe ₂ O ₃	51	30-60
Al ₂ O ₃	15	10-20
CaO	13	2-8
SiO ₂	10	3-50
Na ₂ O	0.20	2-10

A viscosity modifying admixture called GLENIUM STREAM 2 was used to induce the flow without segregation. GLENIUM STREAM 2 is dosed at the rate of 50 to 500ml/100Kg of cementations material. Other dosages may be recommended in special cases according to specific job site conditions. GLENIUM STREAM 2 consists of a mixture of water soluble polymers which is absorbed on to the surface of cement granules thereby changing the viscosity of water and influencing the rheological properties of the mix. It also resist the segregation due to aggregation of the polymer chains when the concrete is not moving. GLENIUM STREAM 2 is a chloride free admixture. It should be added to the concrete after all the other components of the mix. This is particularly important in order to obtain maximum efficiency. It is a colorless free flowing liquid and manufactured by BASF Construction Chemicals (India) Pvt. Ltd., Pune.

A high performance concrete superplasticizer based on modified polycarboxylic ether was used in the experimentation. The trade name of the superplasticizer is GLENIUMTM SKY 784. It greatly improves the cement dispersion. It is manufactured by BASF Construction Chemicals (India) Pvt. Ltd., Pune. Optimum dosage of GLENIUMTM SKY 784 should be determined in trial mixes. As a guide a dosage range of 300ml to

1200ml per 100kg of cementations material is normally recommended..

III. EXPERIMENTAL PROCEDURE

The cement, sand and coarse aggregates were weighed according to the mix proportion 1:1:0.5. The flyash and cement proportion used in the experimentation was 1:3.5. To this dry mix the required quantity of red mud (0%,1%, 2%, 3%, 4%, 5%, 6%, 7%, 8%, 10%, 12%, 15% and 16%) was added and homogenously mixed. To this dry mix the 33% of water was added and thoroughly mixed. To this the superplasticizer was added at the rate of 700ml/100Kg of cementitious material and mixed intimately. Now the viscosity modifying agent (VMA) was added at the rate of 100ml/100Kg of cementitious material. The entire mix was thoroughly mixed once again. At this stage, almost the concrete was in a flowable state. Now, the flow characteristic experiments for self compacting concrete like slump flow test, was conducted.

After conducting the flow characteristic experiments the concrete mix was poured in the moulds required for the strength assessment. After pouring the concrete into the moulds, no compaction was given either through vibration or through hand compaction. Even the concrete did not require any finishing operation. After 24 hours of casting, the specimens were demoulded and were transferred to the curing tank wherein they were allowed to cure for 28 days


For compressive strength assessment, cubes of size 150mmX150mmX150mm were prepared. After 28 days of curing the specimens were tested for their compressive strengths

IV. RESULTS AND ANALYSIS


The following TABLE-3. gives the overall results of compressive strength of self compacting concrete containing the combination of admixtures (SP+VMA) for various percentage addition of red mud

TABLE-3. Variation of Compressive Strength w.r.t. Red Mud Percentage

Percentage addition of red mud	Compressive strength (MPa)	Percentage (%) increase or decrease of compressive strength w.r.t. ref mix (%)
0	40.59	-
1	41.18	+1.45
2	44.29	+9.11
3	42.66	+5.10
4	40.29	-0.74
5	37.62	-7.32
6	35.11	-13.50
7	34.51	-14.98
8	33.62	-17.17
10	32.84	-19.09
12	32.08	-20.97
15	31.56	-22.25
16	31.38	-22.69



Graph 1 The variation of compressive strength of SCC containing red mud



Graph 2 Variation of compressive strength of SCC containing red mud

V. CONCLUSIONS

- In India, HINDALCO'S aluminium refinery in Belgaum, Karnatka generates a voluminous quantity of industrial waste in the form Red Mud, almost 400,000 tonnes per annum. This is largely dumped at sites, which are referred to as red mud pounds. The volume of waste generated is large and its alkalinity has the potential to contaminate valuable surface and surface and groundwater resources.
- So this mix (Red Mud + SCC) should be used for the construction activity it will reduce the problem of environmental pollution at the same time it reduce the cost of the construction and add it makes the concrete high performing from the durability point of view.
- It has been observed that the compressive strength of self compacting concrete produced with the combination of admixtures such as (SP+VMA) goes on increasing up to 2% addition of red mud. After 2% addition of red, the compressive strength starts decreasing compacting is the compressive strength of self compacting concrete produced with (SP+VMA) is maximum when 2% red mud is added. The percentage increase in compressive strength at 2% addition of red mud is + 0.11 thus, it is observed that maximum compressive strength of self compacting with the combination of admixtures (SP+VMA) may be obtained by adding 2% red mud.
- The compressive strength of concrete increases with the addition of Red Mud up to 2% then reduces and comes to no increase at almost 4% addition. So it can be concluded that on addition of 4% may be made to SCC without any loss to its compressive strength.

VI. ACKNOWLEDGEMENTS

First and foremost, I wish to express my sincere apperition to my honorable Supervisor, Dr. Saleem Akhtar, Professor and Head of Civil Engineering Department, University Institute of Technology (RGPV) Bhopal, Second and foremost, I wish to express my sincere apperition to my honorable Supervisor, Mr. Survesh Rajput, Assit Prof. Department of Civil Engineering, MANIT, Bhopal for his helpful contribution in my Thesis work. He is an intellectual in creativity, analysis, comprehension and has a great source of idea about this project. His suggestions, encouragement and guidelines played a vital role in my thesis work. Without his inspiration, cooperation and support it was not possible to complete this paper.

REFERENCES

Journal Papers:

- [1] Ouchi, M., M. Hibino, and H. Okamura, "Effect of Superplasticizer on Self-Compactability of Fresh Concrete", TRR 1574, pp.37-40 (1996)
- [2] Okamura, H, "Self-Compacting High-Performance Concrete", Concrete International, pp.50-54 (1997).
- [3] Ozawa, K., "Development of high performance concrete based on the durability design of concrete structures", EASEC-2, Vol. 1, pp.445-450 (1989)

Books:

- [4] Bartos, J. M., "Measurement of Key Properties of Fresh Self-compacting Concrete", CEN/PNR Workshop, Paris (2000)
- [5] Mauskar, J. M., "Assesment of Utilization of Industrial Solid Waste in Cement Manufacturing" Central Pollution Control board , Delhi (2006).

